

Rust preventives

Product Name	Appearance Color	ASTM	Density	Viscosity	Flash Point	Film Thickness	Prevention Period	Characteristic and Application
NONRUSTER P307	Brown transparent	6.5	0.88	4.5	42	6.4	6 month	For general purpose, in process rust prevention of bearings
NONRUSTER P307D	Brown transparent			1.9	51	0.6	1 month	For short term in house rust prevention
NONRUSTER P313	Brown transparent	3.0	0.87	5.5	102	2	4 month	For mid term in house rust prevention with excellent water displacement property
NONRUSTER ACR	Yellow transparent		1.05	13	None		1 week (5%)	Dilute with deionzed water from 3-5 % for short term rust prevention